



WALKI®Wall Breath



Product Data sheet

Standard

EN 13859

Description

WALKI®Wall Breath is non-woven / polymer / non-woven laminate. It is UV stable and water-repellent.

Applications

WALKI®Wall Breath is designed to be used in walls as vapour-permeable layer. Installation in accordance with the guidelines for waterproof and vapourpermeable membranes.

Notified test laboratory

SP Technical Research Institute of Sweden
Västerås
Brinellgatan 4
SE-50462 Borås

Typical Characteristics

Property	Test Method	Units	Value	Tolerance
Grammage	ISO 536	g/m ²	71 (-2 / +2)	± 15 %
Sd value	EN ISO 12572	m	0,1	0,5
Air transmission	EN 12114	m ³ /m ² ,h,Pa	0,018 - 0,019	≤ 0,1
Tensile strength MD	EN 12311-2	kN/m	2,9 (TTV -14%)	TTV ± 20%
Tensile strength CD	EN 12311-2	kN/m	1,8 (TTV -5%)	TTV ± 20%
Elongation CD	EN 12311-2	%	64 (TTV ±0%)	TTV ± 20%
Elongation MD	EN 12311-2	%	77 (TTV -14%)	TTV ± 20%
Tear Strength MD	EN 12310-1	N	62 ±3	≥ 20
Tear Strength CD	EN 12310-1	N	64 ±3	≥ 20

Walki Oy – Juho Hyytiäinen

Walki Oy
FIN-37601 Valkeakoski
Tel +358 (0)205 36 3111
Fax +358 (0)205 36 3090

Certification:
DIN EN ISO 9001:2000
DIN EN ISO 14001:2005
OHSAS 18001

www.walki.com
firstname.lastname@walki.com